


FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 28 2009 10:18AM P4



DIVERSIFIED
TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 23, 2009

ROLAND DIGITAL GROUP AMERICA
15363 Barranca Parkway
Irvine, CA 92618

Reference: Flammability Test Report
Lab Identification No. 9676
Invoice No. 22019 (Attached)

Dear Sirs:

One (1) sample, identified as, **FRSB**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Flame Propagation of Textiles and Films, 2004 Edition, (Test 2, Large Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Afterflame</u> <u>(seconds)</u>	<u>Residual Flame</u> <u>(seconds)</u>	<u>Char Length</u> <u>(inches)</u>
Single 1	0.0	0.0	10.0
Flat 2	0.0	0.0	11.0
Specimen 3	0.0	0.0	11.0
4	0.0	0.0	13.0
5	0.0	0.0	14.0
6	0.0	0.0	10.0
7	0.0	0.0	12.0
8	0.0	0.0	11.0
9	0.0	0.0	10.0
10	0.0	0.0	11.0

The sample submitted meets the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,



Karon S. Matkins

KSM/mr
Attachment

FROM : DIVERSIFIED TESTING LABS

FAX NO. : 3362271175

Apr. 28 2009 10:17AM P2



DIVERSIFIED
TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 23, 2009

ROLAND DIGITAL GROUP AMERICA
15363 Barranca Parkway
Irvine, CA 92618

Reference: Flammability Test Report
Lab Identification No. 9676
Invoice No. 22019 (Attached)

Dear Sirs:

One (1) sample, identified as, BOSS, was received and tested in accordance with the National Fire Prevention Association No. 701, "Flame Propagation of Textiles and Films, 2004 Edition, (Test 2, Large Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Afterflame</u> <u>(seconds)</u>	<u>Residual Flame</u> <u>(seconds)</u>	<u>Char Length</u> <u>(inches)</u>
Single 1	0.0	0.0	10.0
Flat 2	0.0	0.0	11.0
Specimen 3	0.0	0.0	12.0
4	0.0	0.0	9.0
5	0.0	0.0	12.0
6	0.0	0.0	11.0
7	0.0	0.0	12.0
8	0.0	0.0	9.0
9	0.0	0.0	12.0
10	0.0	0.0	10.0

The sample submitted meets the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,


Karón S. Matkins

KSM/mr
Attachment